

Pumatect

High build gloss finish
epoxy resin floor coating


Industrial Floor Treatments (Stone) Ltd
PO Box 3701, Stone, Staffordshire, ST15 9ES
Tel: 01785 819800

enquiries@iftstone.co.uk

www.iftstone.co.uk



Resin Development



Description

Pumatect is a two-component virtually solvent free epoxy floor coating offering excellent abrasion and chemical resistance.

Pumatect provides a tough, hard wearing coating for medium duty traffic giving high film build and wear resistance.

Thickness

Pumatect has a dry film thickness of approximately 400 microns from two coats - this is the equivalent of up to 12 coats of leading single pack floor paints.

Category

Pumatect is a Type 3 floor coating (BS 8204-6)

Appearance

Pumatect has a gloss finish and is available in a range of attractive colours.

Typical Uses

Pumatect is designed for use in medium duty areas requiring an easy to clean, tough and durable floor coating with excellent chemical resistance e.g. warehouses, factories, workshops, showrooms, packing and storage areas.

Pumatect can also be used as a seal coat for broadcast systems such as Intermediate Car Park Decks.

Pumatect is suitable for regular foot traffic, frequent fork lift truck traffic and occasional hard plastic-wheeled trolleys.

Features & Benefits

- Protects concrete from oil and chemical spillages
- High build with excellent wear resistance
- Virtually solvent free
- Gloss, easy to clean finish
- Non-dusting

Pack Size

5, 10, 15 and 25 kg units.

Adhesion to concrete (BS EN 1504-2) >1.5 MPa (concrete failure)

The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary dependent upon site conditions.

Suitable Substrates

Concrete and polymer modified cementitious screeds.

Cure Schedule at 20°C

Working life of full packs * 25 minutes

* Usable working life of material following mixing and immediate spreading as per the application instructions.

Finished floor *

Over-coating time	16 - 36 hours
Cure time to pedestrian traffic	24 hours
Full chemical resistance	7 days

The floor should be protected from contact with water for at least 7 days.

* The above cure times are approximate and given as a guide only. These times can vary due to prevailing site conditions. At lower temperatures curing times will be extended. If the over-coating interval of 36 hours is extended, the first coat should be abraded to ensure inter-coat adhesion.

Coverage

The coverage rate will vary depending on the texture and porosity of the substrate, film thickness and application technique.

Two coats are normally sufficient but on very porous substrates an initial coat of **Pumaprime SF** may be required. As a guide:

Normal substrate:	1 st coat - 375 g/m ²
	2 nd coat - 250 g/m ²

Resdev Limited

Pumafloor House, Ainleys Industrial Estate
Elland, West Yorkshire, HX5 9JP, England
Tel: +44 (0) 1422 379131
fax: +44 (0) 1422 370943
info@resdev.co.uk
www.resdev.co.uk



Resin Development

Pumatect
Medium duty epoxy floor coating
Page 1 of 3
27/03/14

Colours Available*

Pumatect is available in a selection of standard colours. A large selection of BS 4800 or RAL colours are available upon request.

* **Pumatect** is not 100% colour fast and may yellow over time. The rate of change will depend on UV light and heat levels and cannot be predicted. This will be more pronounced with lighter colours and blue shades and does not compromise the product's performance or chemical resistance characteristics.

Application Conditions

Pumatect is a relatively viscous coating. Do not apply outside of the range 10°C to 25°C. Localised heating or cooling equipment may be required outside this range to achieve ideal temperature conditions.

To reduce the risk of "surface blooming" caused by condensation, the climate above the uncured floor should be maintained at least 3 °C above the dew point for at least 48 hours after application.

Surface Preparation Concrete

The concrete substrate must be sound with a minimum compressive strength of 25 N/mm² and a minimum pull off strength of 1.5 N/mm².

It should be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

It must have dried out to give maximum moisture readings of 75% RH or 5% by weight. If this has not been achieved works may still be able to proceed after application of a surface DPM.

Inadequate preparation will lead to loss of adhesion and failure. In coatings, there is a tendency for the finish to mirror imperfections in the substrate. Grinding, or light vacuum-contained shot-blasting is therefore preferred over planing for these systems.

Percussive scabbling or acid etching is not recommended. Refer to the Resdev Guide to Surface Preparation for further information.

Concrete must include a functional damp-proof membrane.

Mixing

Materials should be stored at 15°C to 25°C for a minimum of 8 hours prior to use.

Pre-mix the coloured resin component before use. Add the hardener component to the coloured resin component and mix using a low speed electric mixer (200 - 500 rpm) for at least 3 minutes until homogeneous.

Use a spatula to scrape the sides and bottom of the mixing vessel several times as unmixed material will result in uncured patches in the final finish.

Pot Life

Mixed material must be used immediately. When mixed, a chemical chain reaction takes place which creates heat and further reduces pot life. High ambient temperatures will reduce pot life.

Application

Best results are obtained in warm conditions (minimum 15°C). Apply with a medium pile simulated sheepskin roller working well into the surface taking care not to exceed the coverage rate. Edges and difficult to reach areas may be applied thinly by brush.

Tool Cleaning

Tools and equipment should be cleaned whilst the resin is still wet with a suitable solvent.

Anti-Slip

An anti-slip finish may be achieved by fully sprinkling the first coat with kiln dried silica sand at 3 - 4 kg/m². Allow the first coat to fully cure (24 hours at 15°C or longer in colder temperatures) then remove all excess sand with a stiff broom and vacuum and apply a second coat to encapsulate the grains. Coverage rate will depend on surface profile but will be significantly greater than for the first coat. As a guide:

Sand Grading (approximate)	m ² /kg (minimum)
0.2 - 0.4 mm	3.5
0.3 - 0.6 mm	2.5
0.7 - 1.2 mm	1.5

Note: These coverage figures are approximate as silica sand grading can vary widely as can site conditions. If in doubt, order extra material to account for wastage or install a test area prior to starting works.

General Maintenance

Pumatect can be easily cleaned using industry standard cleaning chemicals and techniques designed for epoxy resin flooring. Test cleaning agents prior to use. Do not steam clean or subject to temperatures in excess of 60°C.

Precautions

Remove food products from the area during application and curing. As with all high gloss paint finishes, scratching of the surface may occur with use due to surface contamination and abrasion. In common with all smooth floor finishes,

Pumatect may become slippery under certain conditions. In areas of chemical spillage, please consult our Technical Department for specific advice.

Technical Advice

For further information on this or any other Resdev product, please contact our office.

The information contained in this document, and all further technical advice given is based on our present knowledge and experience. However, it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application are beyond our control. Properties listed are for guidance purposes only. We reserve the right to make any changes according to technological progress or further developments.

Resdev Limited

Pumaflor House, Ainleys Industrial Estate
Elland, West Yorkshire, HX5 9JP, England
Tel: +44 (0) 1422 379131
fax: +44 (0) 1422 370943
info@resdev.co.uk
www.resdev.co.uk



Resin Development

Pumatect
Medium duty epoxy floor coating
Page 2 of 3
27/03/14

Health and Safety

Before using this product, please ensure that you have received and read the product Safety Data Sheet. Refer to hazard labelling on the product. Wear gloves and avoid contact with skin and eyes.

EU Directive 2004/42/EC

Complies with category j type SB (< 500 g/l).

Storage

Materials should be kept dry and stored in a weatherproof building maintained at 15°C to 25°C on pallets and away from walls. Consignments should be used in order of batch number. Protect from frost.

Shelf Life *

12 months if stored in accordance with the above recommendations.

Limitations

Do not proceed with application if atmospheric relative humidity is, or is anticipated to be >75% or if the surface temperature is <3°C above the dew point. Application should not commence when the substrate temperature or the ambient temperature is, or is anticipated to be <10°C during the application or within the curing period.

The manufacture of **Pumatect** is a batch process and despite close manufacturing tolerances, minor variations in shade may occur between batches. Products from different batches should not be used on the same surface or surfaces close together. If mixed batches are unavoidable, it is best practice to use the different batches only in areas where the colour cannot be directly compared. Touching up should only be attempted using product from the same batch using the same application methods. Product should be reserved specially for this purpose. It is recommended that touching up is carried out up to a break in the floor or surface.

Resdev Limited, Pumaflor House, Ainleys Industrial Estate Elland, West Yorkshire, HX5 9JP, England			
CE		13	DOP RV0026
EN 13813 SR-B2,0-AR0,5-IR9 Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations			
Reaction to fire	NPD	Impact resistance	IR9
Release of corrosive substances	SR	Sound insulation	NPD
Water permeability	NPD	Sound absorption	NPD
Wear resistance	AR0,5	Thermal resistance	NPD
Bond strength	B2,0	Chemical resistance	NPD

The information contained in this document, and all further technical advice given is based on our present knowledge and experience. However, it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application are beyond our control. Properties listed are for guidance purposes only. We reserve the right to make any changes according to technological progress or further developments.

Resdev Limited

Pumaflor House, Ainleys Industrial Estate
Elland, West Yorkshire, HX5 9JP, England
Tel: +44 (0) 1422 379131
fax: +44 (0) 1422 370943
info@resdev.co.uk
www.resdev.co.uk



Resin Development

Pumatect
Medium duty epoxy floor coating
Page 3 of 3
27/03/14